

S393 Thermal Conductive Pad



Feature





- Very good thermal conductivity
- Soft and high compressibility
- Natural tack
- Easy to assemble
- Good insulator

特性

- 良好的導熱性
- 柔軟及高壓縮性
- 自粘
- 容易施工
- 超高耐電壓

Application 產品應用端

- Electronic components: IC、CPU、MOS
- LED、M/B、P/S、Heat Sink、
- LCD-TV、Notebook PC、PC、Telecom Device、Wireless Hub..... etc.
- DDR II Module、DVD Applications、Hand-set applications..... etc.



Testing sample thickness: 1.5mm

In "Thermal resistance V.S. Pressure V.S. Deflection" chart, S393 provide low thermal impedance. The pressure gets higher, the thermal impedance gets lower, and deflection percentage gets higher. S393 provide good compliance and softness.

Property	S393	Unit	Tolerance	Test
Color 顏色	Light Green 淺綠	-	-	Visual
Thickness 厚度 (Gap is 0.1mm, 間隙0.1mm) (The thickness can be ordered 可依客戶所需厚度生產)	0.3~20	mm 公厘	-	ASTMD 374
	0.0118~0.787	inch 公吋	-	ASTMD 374
Thermal Conductivity 導熱係數	3.5	W/m.k	-	ASTME 1530
Flame Rating 耐燃等級	94V-0	-	-	UL
Insulation Strength 耐電壓值	>8	kv	-	ASTMD 149
Weight Loss 重量損失	<1	%	-	After 24hrs at 200°C
Specific Gravity 比重	2.35	g/cm³	±0.2	ASTMD 792
Working Temperature 工作溫度	-40~+200	°C	-	-
Surface Resistance 表面阻抗	1.25x10 ¹⁴	ohm	-	ASTMD 257
Elongation 延展率	180	%	±0.2	ASTMD 412
Tensile Strength 抗拉強度	7	Kgf/cm²	±0.5	ASTMD 412
Standard Shape 標準形狀	-	Sheet ones 單片狀	-	-
Hardness 硬度	11	Shore A	±3	ASTMD 2240
REACH Compliant 符合REACH 規範	Yes 是	RoHS Compliant 符合RoHS 規範	Yes 是	Yes 是

● Available to apply adhesive 可依需求背膠

● Pre-cut for different shape 可依需求沖型裁切

● Need sample? 樣品需求



S393 - 15 - 20 - 3 - 1A, 20

- Choose the P/N.
- Fill the size: x,y,z.
- Apply the adhesive or not? 0=none, 1A=one side, 2A= two sides.
- Fill the quantity you need.

t-global 高柏科技有限公司 T-GLOBAL TECHNOLOGY CO., LTD

TECHNOLOGY

www.tglobal.com.tw service@tglobal.com.tw

Service Center: 0800211298 TEL: +886-2-26702575 FAX: +886-2-86776762

Copyright 2009 by T-Global Technology Co., Ltd